

TONON
made in Italy www.tononitalia.com

leathers
& freeform

Soft category 9



Soft 117



Soft 195




Soft 179



Soft 501




Soft 158



Soft 502




Soft 199



Soft 96



Soft 207




Soft 97



Soft 176



Soft 526



Soft 504



Soft 505



Soft 140




Soft 175




Soft 147

Soft category 9



Soft 542



Soft 520



Soft 192



Soft 522



Soft 545




Soft 543



Soft 98



Soft 160



Soft 563



Soft 532



Soft 534



Soft 188



Soft 557



Soft 566



Soft 564



Soft 203



Soft 559



Soft 112



Soft 141



Soft 101

Tender category 7



Tender 617



Tender 695



Tender 267



Tender 621



Tender 265



Tender 266



Tender 674



Tender 605



Tender 608



Tender 268



Tender 202



Tender 203



Tender 210



Tender 602



Tender 258



Tender 220



Tender 603



Tender 218



Tender 692



Tender 619



Tender 684



Tender 209



Tender 672



Tender 608



Tender 215



Tender 615



Tender 612



Tender 614

Structur category 7



S00



S78



S82



S55



S56



S51



S72



S04



S49



S23



S48



S52



S02



S12



S53



S39



S31



S13



S71



S44



S26

Freeform



Freeform X04



Freeform X02




Freeform X05



Freeform X09



Freeform X03



Freeform X07



Freeform X08



Freeform X10



Freeform X06



Freeform X01

Soft category 9

Thickness		1,1/1,2 mm
Origin		Raw Hides
Place of origin		European
Tanning		Chrome salts
Dyeing		Aniline through-dyeing
Finishing		Water-based pigments
Typology		Grain slightly corrected
Light fastness xenon lamp	UNI EN ISO 105 B02	Value > 4 Blu scale
Tear strenght	UNI EN ISO 3377-1	> 28 N/mm
Dry rub fastness	ISO 11640	500 cycles value 4 grey scale
Wet rub fastness	ISO 11640	80 cycles value 5 grey scale
Flex crack resistance	ISO 5402	25000 cycles
Adhesion of finish	UNI EN ISO 11644	> 7,5 N/cm
<i>Certificato n° H04455 - 2008 - Dedalo Srl (Arzignano - VI)</i>		
Fire resistance	British Standard BS 5852 Part 1 (1979) N° 0: Cigarette Test N° 1: Match Test	Passa

Tender category 7

Thickness		0,9/1mm
Origin		Raw Hides
Place of origin		European
Tanning		Chrome salts
Dyeing		Aniline
Finishing		Water-based pigments
Typology		Half grain on bovine printed smooth
Light fastness xenon lamp	UNI EN ISO 105 B02	Value > 8 Blu scale
Tear strenght	UNI EN ISO 3377-1	> 29 N/mm
Dry rub fastness	ISO 11640	500 cycles value 4/5 grey scale
Wet rub fastness	ISO 11640	250 cycles value 4/5 grey scale
Flex crack resistance	ISO 5402	> 50000 cycles
Adhesion of finish	UNI EN ISO 11644	> 10,20 N/cm
<i>Certificato n° H04454 - 2008 - Dedalo Srl (Arzignano - VI)</i>		
Fire resistance	British Standard BS 5852 Part 1 (1979) NI/0: Cigarette Test NI/1: Match Test	Passa

Due to technical reasons it is not possible to guarantee the same tonality of colour from one lot to another.

Structure category 7

<i>Thickness</i>		<i>1,4/1,6 mm</i>
<i>Origin</i>		<i>Raw Hides</i>
<i>Place of Origin</i>		<i>European - South American</i>
<i>Tanning</i>		<i>Chrome salts</i>
<i>Dyeing</i>		<i>Aniline through-dyeing</i>
<i>Finishing</i>		<i>Water-based pigments</i>
<i>Typology</i>		<i>Grain slightly corrected and printed</i>
<i>Light fastness xenon lamp</i>	<i>UNI EN ISO 105 B02</i>	<i>Value > 7 Blu scale</i>
<i>Tear Strenght</i>	<i>UNI EN ISO 3377-1</i>	<i>> 89 N/mm</i>
<i>Dry rub fastness</i>	<i>ISO 11640</i>	<i>500 cycles value 4 grey scale</i>
<i>Wet rub fastness</i>	<i>ISO 11640</i>	<i>250 cycles value 4/5 grey scale</i>
<i>Flex crack resistance</i>	<i>ISO 5402</i>	<i>> 50000 cycles</i>
<i>Adhesion of finish</i>	<i>UNI EN ISO 11644</i>	<i>9,3 N/cm</i>
	<i>Certificato n° H02294 - 2008 - Dedalo Srl (Arzignano - VI)</i>	
<i>Fire resistance</i>	<i>British Standard BS 5852 Part I (1979) NI/C: Cigarette Test NI/1: Match Test</i>	<i>Passa</i>